




YUASA NPC SERIES MAINTENANCE-FREE LEAD-ACID BATTERIES



Innovative valve-regulated cyclic specialty now available with doubled longer life.

YUASA BATTERY CO., LTD.

JAPAN

YUASA NPC SERIES


The maintenance-free and valve regulated constructions combine with heavy-duty plates and unique separator systems to make NPC serviciable twice as long as conventional counterparts.

YUASA WUASA BARTEMATYEE EMARIME MITER CYCLIC APPLICATION MPC15-12 12V 15Ah COMMERCE TO AN AUTUS COMMERCE TO AUTUS COMMERCE TO AN AUTUS COMMERCE TO

FEATURES

1. Doubled cycle life

NPC operates 500 charge/discharge cycles or twice as many cycles as conventional cycle use batteries at 75% D.O.D. (depth of discharge).



2. Valve-regulated and maintenance-free

Battery electrolyte retained solidly in the separator and the innovative gas recombinant system allow minimum gas emittance freeing from maintenance.

3. Durability for deep discharge use

Yuasa's state-of-the-art plate barrier prevention and the unique separator systems help endure deep discharge use and thus considerably prolonging battery's service life.

4. Minimal self-discharge

Cyclic use batteries tend to be left discharged after usage causing plate corrosion leading to shortened life. Self discharge rate of NPC is as small as only 0. 1% a day at 20°C as shown in the diagram and thus extends storage period remarkably long.

■Operating temperature range

Charge: $-15\sim50^{\circ}\text{C} \ (5\sim122^{\circ}\text{F})$ Discharge: $-15\sim50^{\circ}\text{C} \ (5\sim122^{\circ}\text{F})$ Storage: $-20\sim50^{\circ}\text{C} \ (-4\sim122^{\circ}\text{F})$

■ Recommended charging method at 25°C (77°F)

Current: Max. 0.25CA Voltage: 14.6~14.8V

■Standard terminal: Bolt/nut
Housing material: ABS resin

APPLICATIONS

Wheelchairs

Golf trolly

Golf carts

OA

ΑV

Lawn mowers

Lights

Toy cars

Sprayers

Photovoltaics

Movable bed

Models

Robots

Communications

Camping accesories

Fishing reel

Fish finders

Electric tools

Pumps


Measuring instruments

AGV


Magnetic lifts

PERFORMANCE


■CYCLE SERVICE LIFE IN RELATION TO DEPTH OF DISCHARGE




ESELF-DISCHARGE CHARACTERISTICS



■DISCHARGE CURRENT VS. DURATION TIME



■DISCHARGE CHARACTERISTICS AT VARIOUS CURRENTS (25°C (77°F))



SPECIFICATIONS

Model	V	Capacity at 20HR (Ah)	Dimensions mm (inch)			Approx.	Terminal
			L	W	Н	wt. Kgs. (pounds)	remina
NPC15-12	12	15	181 (7.13)	76 (2.99)	167 (6.57)	6.3 (13.89)	Bolt/nut
NPC24-12	12	24	175 (6.89)	166 (6.54)	125 (4.92)	9.0 (19.84)	Bolt/nut
NPC38-12	12	38	197 (7.76)	165 (6.50)	170 (6.69)	14.2 (31.31)	Bolt/nut

IMPORTANT HINTS TO PROLONG BATTERY LIFE

■ RECOMMENDED CHARGING **INSTRUCTIONS**

- 1. Constant voltage charging is recommended at 14.6 to 14.8 volts at 25°C (77°F).
- 2. Initial charging current: Max. 0.25CA.
- 3. Always recharge battery after use.
- 4. Optimum charged volume is 110% of discharged volume.

Optimum charging time: 9 hours Maximum charging time: 20 hours

- 5. When using a charger other than the constant voltage type, be alert with charging hours, charging voltage and current.
- 6. Try to apply the least internal resistance cable, considering line drop voltage.


■DISCHARGING

- 1. Never leave battery in a discharged condition, or at less than 11.8V OCV. If left discharged below OCV 11.8V, battery may not restore full charge and permanently lose service life.
- 2. Optimum discharge current is less than ICA. The higher the current, the less the capacity.
- 3. Permissable discharge current is 3C. If 3C or more current is applied, consult us for our operating recommendation.
- 4. If battery is to be stored for a long time, apply supplementary charge according to the table, right.

OTHERS


- 1. Keep battery in a dry and cool place within the temperatures of -20°C to 50°C (-4 to 122°F)
- 2. Do not locate near fire. Avoid short circuit.

SCONSTANT CURRENT, CONSTANT VOLTAGE CHARGING CHARACTERISTICS



If battery is overdischarged, initial charging current may be minimal, but will recover normal value in an hour or so.

MAMBIENT TEMPERATURE VS. CAPACITY



INTERVAL OF SUPPLEMENTAL CHARGE AT VARIOUS STORAGE TEMPERATURES

Storage Temp.	Charging interval		
20°C (68°F)or less	Once in 9 months		
20~30°C (68~86°F)	Once in 6 months		
30~40°C (86~104°F)	Once in 3 months		

Try to avoid usage at 40°C or more to maximize battery life.

Specifications subject to change without prior notice.



YUASA BATTERY CO., LTD.

12-11, Higashi - Shimbashi 2-Chome Minato-ku, Tokyo, 105, Japan Phone: Tokyo (03) 3437-2438 Cable: YUASABATRY TOKYO

Telex YBCTOK AJ29228

Facsimile: Tokyo (03) 3433-7375 GIII

Distributor: